



TESTORS® ALL PURPOSE MATTE CRAFT PAINT

DESCRIPTION AND USES

Testors® All Purpose Matte Craft Paints are high quality waterbase paint for general craft use and decorative paint. For use on wood, artist's canvas, plaster, clay, metal, fabric, bisque, and more.

PRODUCTS

SKU	DESCRIPTION (2 Oz.)
292421A	Black
292422A	Fuchsia
292423A	Green
292424A	Orange
292425A	Purple
292426A	Hazey
292427A	Sunshine
292428A	Island Breeze
292429A	Stop Sign
292430A	White
292594	Petal Pink
297419	Turquoise
297430	Navy Blue
297431A	Royal Blue
297434	Paradise
297438A	Browne
297439	Earthy
297447	Shamrock
297450	Avocado
297457	Passion Fruit
297461	Plum
297466	Engine Red
297467	Ruby
297478	Seafoam
297479	Coral Cove
297481	Deep Sea
297482	Dark Plum
297484	Blue Fog
297485	French Vanilla
297843	Coffee

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants. Rinse with fresh water and allow to thoroughly dry.

APPLICATION

Pour paint into a small paper or plastic cup. Dip paint brush into the paint and wipe the brush against the sides of the cup before applying to surface. If thinning is needed, add water into cup in very small amounts and stir until desired paint thickness is achieved.

DRY AND RECOAT TIMES

Based on 25°C (77°F) and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 30 minutes, to handle in 1-2 hours, recoat in 3 hours and fully cured in 24 hours.

COVERAGE

Up to 6 sq. ft. per 2 ounce bottle.

CLEAN UP

Clean brush and other application tools immediately with soap and water.



**TESTORS® ALL PURPOSE
MATTE CRAFT PAINT**

PHYSICAL PROPERTIES

		TESTORS MATTE CRAFT PAINT
Resin		Acrylic WB Emulsion
Pigment		Varies by color
Solids By Volume		20-30%
VOC		<120 g/l
Recommended Dry Film Thickness (DFT) per Coat		1 mil
Wet Film to Achieve DFT (unthinned material)		3.5-5 mils
Practical Coverage at Recommended DFT (assumes 15% material loss)		4-6 sq.ft./per 2 oz. bottle
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	30 minutes
	Handle	1-2 hours
	Recoat	3 hours
	Full Cure	24 hours
Shelf Life		3 Years
Flash Point		>200°F (>93°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.